

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(12) **UK Patent Application** (19) **GB** (11) **2 193 469** (13) **A**

(43) Application published 10 Feb 1988

(21) Application No 8718099

(22) Date of filing 30 Jul 1987

(30) Priority data

(31) 8618595
8619245

(32) 30 Jul 1986
6 Aug 1986

(33) GB

(51) INT CL⁴

B41M 1/18 // 1/2

(52) Domestic classification (Edition J):

B6C 307 SAB

U1S 1370 1594 1676 2279 2286 3044 B6C

(56) Documents cited

"British Printer" Dec 1985 pages 55, 56, Sept 1981
page 53

(71) Applicant

Small Products Limited

(Incorporated in United Kingdom)

Thames House, 566 Cable Street, London E.1

(58) Field of search

B6C

Selected US specifications from IPC sub-class B41M

(72) Inventors

Richard Frederick Small
Lascelle Augustus Barrow
Barry Martin Dix
Dakshesh Shashikant Patel

(74) Agent and/or Address for Service

E. Eder & Co.
39 Cranbrook Road, Ilford, Essex IG1 4NH

(54) **Silk screen printing**

(57) A method of silk screen printing on a sheet of paper or board e.g. for posters, characterised in that a first silk screen printing is effected on the sheet utilising a printing ink that produces minimal curl, and in that at least one subsequent silk screen printing is effected on the sheet utilising a water-based printing ink. The first printing step may use non-aqueous printing ink curable by irradiation, an organic solvent-based printing ink, or an aqueous ink of low water (<20%) and high solids content. The subsequent printing step may use irradiation curable ink. Enables water based inks to be used as additional colours without producing unacceptable curl of the paper i.e. without preventing feeding of the printed sheet again through the screen printing machine.

GB 2 193 469 A

SPECIFICATION

Improvements in or relating to printing

- 5 This invention relates to printing and in particular to screen printing (commonly known as silk screen printing). As is well known, the silk screen printing process involves the use of a screen of silk, polyester, nylon, metal gauze or any other suitable mesh-like or perforated material. For convenience (and for consistency with the terminology historically employed in this art) the term "silk screen printing" will be used herein and it will be appreciated that no restriction to "silk" material is thereby intended. 10
- Although silk screen printing is a very old technique, it still has numerous problems and/or limitations associated with it. For example, where several large-size multi-colour sheets are to be silk screen printed for, say, a poster to be pasted up on a hoarding, large quantities of printing inks are needed which are expensive.
- 15 The printing inks required for screen printing are quite different from those to be used for other forms of printing. The screen printing inks being generally used at present are organic solvent-based and usually contain ethyl or nitro cellulose resins. They are dried in warm air tunnels by driving off the organic solvents, and are thus potentially hazardous to the printing operatives. Another problem which arises with such organic solvent-based screen printing inks, 20 relates to solvent loss from the ink on the printing screen whereby the ink increases in viscosity and after a certain period of time will not properly pass through the open areas of the printing mesh. This "drying in" results in loss of printed image and is described as screen stability, i.e. inks with poor screen stability "dry in" rapidly.
- Recent developments over the last ten years have seen the introduction of Ultra-Violet-curing screen process inks. Here the formulations use raw materials which do not increase in their viscosity on the printing screen but instead dry by exposure to intense Ultra Violet light. This means that this type of ink has almost unlimited screen stability compared to non-UV curing, organic solvent-based, screen printing inks. However, such UV-curing inks are expensive, and leave a very thick print coat on the paper surface—particularly where multi-colour, e.g. four-colour, silk screen printing is effected. 30
- Such thick or heavy print images on the surface of a sheet of poster paper often necessitate that for mounting the poster to its hoarding, a special adhesive—which is other than an inexpensive starch-based adhesive—must be used if efficient bonding is to be achieved. A similar problem often arises with the older type of organic solvent-based silk screen printing inks. This adhesion problem is common where the individual sheets overlap, e.g. at overlapping marginal edges of adjacent poster sheets. The back of the top sheet does not have sufficient adhesion to the ink surface printed on the sheet beneath. When the poster paste dries out, the top sheet of the overlap often curls up and away from the sheet underneath. The problem is particularly severe when the paper is completely covered with several layers of ink. Posters 40 printed with offset litho inks have less tendency to curl when they dry out compared to those produced with screen printing inks. As the screen printing process achieves its high quality print appearance by a much higher ink deposit, the curl problem is pronounced with screen printing inks. Therefore the adhesives used with screen printed posters need to have better adhesion properties to prevent overlap curl.
- 45 Mixtures of one or more starch adhesives and one or more polyvinyl alcohol (P.V.A.) adhesives were investigated by the applicants, and these were found to give a much improved adhesion at the overlapping edges of superimposed sheets as compared to a 100% starch-based adhesive product. However, mixtures of starch and P.V.A. adhesives have the disadvantage of being more expensive and the resultant improved adhesion makes the removal of the total poster from the hoarding more difficult. Thus they are not likely to find favour with bill-posters, i.e. those 50 responsible for putting up the posters on the hoardings.
- It is therefore considered desirable to reduce, if not wholly obviate, some or all of the above-mentioned and/or other disadvantages associated with or relating to prior art screen printing methods and inks.
- 55 According to one aspect of this invention there is provided a method of silk screen printing on a sheet of paper or board, characterised in that a first silk screen printing is effected on the sheet utilising a printing ink that produces minimal curl, and in that at least one subsequent silk screen printing is effected on the sheet utilising a waterbased printing ink.
- By effecting said first printing with an ink that produces minimal curl, the printed sheet can be 60 readily fed again through the screen printing machine to be overprinted with the subsequent printing(s).
- Said first silk screen printing may be effected utilising an organic solvent-based printing ink, or a non-aqueous printing ink that is curable by irradiation, or an aqueous ink of high solid and low water content, e.g. water content less than 20%.
- 65 It is considered that the printing ink used for the first printing in effect seals the surface of the 65

paper sheet thereby reducing the risk of damage to the sheet from the water content of the water-based printing ink.

Preferably the first silk screen printing is in a first colour and the or each said subsequent printing is in a different colour.

- 5 Preferably said water-based printing ink used for the or each subsequent printing is at least partially curable by irradiation. As used herein in relation to curing, the term "irradiation" refers to electromagnetic radiations having wavelengths shorter than those of the visible spectrum. The term thus includes ultra-violet (UV) and electron beam radiations. 5

- 10 Preferably, the water-based printing ink used for the or each subsequent printing comprises one or more photoinitiators and is at least partially curable by irradiation comprising electromagnetic radiations in the ultra-violet light waveband. 10

Alternatively, the water-based ink used for the or each subsequent printing may be at least partially curable by irradiation with an electron beam. Where the ink is curable by irradiation with an electron beam, then photoinitiator(s) may be omitted from the printing ink composition.

- 15 Preferably, and in either case, the water-based printing ink used for the or each subsequent printing is subjected to heat or to thermal radiation, e.g. is subjected to electromagnetic radiations in the infra-red light waveband, prior to curing. Alternatively, the print is subjected to cold air from a jet air dryer or is subjected to microwave or radio frequency drying. 15

- 20 Preferably said water-based ink used for the or each subsequent printing comprises an unsaturated acrylate resin, e.g. a polyester acrylate resin. 20

Advantageously, the water-based screen printing ink used for the or each subsequent printing comprises an emulsion of a resin in water.

- 25 Preferably the emulsion has said resin wholly, or at least substantially, as the dispersed phase and wholly, or at least substantially, insoluble in water, water being the continuous phase of the emulsion. 25

Advantageously said resin comprises 30% to 60% (preferably 50%) of the emulsion.

Preferably said method is employed to screen print a plurality of colours upon a sheet and, after printing, the printed sheet is subjected to corona discharge to render the sheet readily mountable, e.g. upon a hoarding, by use of a starch-based adhesive.

- 30 It is considered that the corona discharge provides miniscule perforations through the printing ink which enable the adhesive to extend through the sheet to provide a "keying" effect facilitating the efficient bonding together of overlapping marginal edges of adjacent sheets. 30

The following relates to the production of individual silk screen printed sheets and their treatment for application onto hoarding sites in accord with embodiments of the present invention. As well as single sheet posters, the embodiments are concerned with the usual combinations of multiple sheet posters (e.g. "16 sheet", "48 sheet" or "96 sheet" posters) for pasting up onto large hoardings. The screen printing method used in these embodiments may be for the production of four colour halftone prints as well as continuous line and tone colour prints.

- 35 The following embodiments of this invention concern the screen ink used to print the sheets. In one preferred form of a "four-colour printing" screen process embodying the present invention, the first colour printed is with a non-aqueous UV-curing printing ink of cyan shade, e.g. a screen ink having a composition in accord with Example 6 below. 35

- 40 In another preferred form of the "four-colour printing" screen process, the first colour printed is with an organic solvent-based printing ink of cyan shade, e.g. a screen ink having a composition in accord with Example 7 below. 40

In yet another preferred form of the "four-colour" screen printing process, the first colour printed is with a slightly aqueous (i.e. less than 20%), predominantly solids (i.e. greater than 80%), screen printing ink of appropriate, e.g. cyan, shade. The screen ink employed for the first printing in this case preferably has a composition in accord with Example 8 below.

- 50 Although in each of these three cases the screen ink employed for the first colour is of cyan shade, it will be appreciated that the colour can be any other primary trichromatic colour, and usually will be the predominant or principal colour produced by the photographic colour separation of the original. 50

- 55 In the following preferred embodiments of the invention, each of the subsequent colours printed in superimposition on the first colour, is screen printed in a water-based, UV-curing ink. In these preferred embodiments the water-based, UV-curing screen ink comprises an emulsion of a resin in water, said resin being wholly (or at least substantially) in dispersed phase and wholly (or at least substantially) insoluble in the water, the water being the continuous phase of the emulsion. Thus the screen printing ink employed for the or each subsequent printing contains water, is water miscible and is water thinnable to a considerable extent, but the water is to be regarded as a carrier or diluent (rendering the ink aqueously reducible in viscosity) rather than as a solvent. Preferably the ink employed for the or each superimposed printing contains at least 40% water. 55

- 60 In a first embodiment of this invention the water-based printing ink employed for the or each printing has a composition comprising an Ultra Violet curing resin emulsified with 60

water, a photoinitiator and an aqueous pigment dispersion. One specific formulation of this, in which the emulsion has the resin amounting to 50% of the emulsion, is given in Example 1.

Example 1

Parts by weight

5			5
	Emulsion Laromer* PE 55W ⁽¹⁾	95.3	
	Darocur* 1173 ⁽²⁾ Photoinitiator	2.0	
10	Aquadisperse Phthalo Blue GB EP ⁽³⁾	2.7	10

15 A composition as formulated in Example 1 was printed through a screen made from 165 threads per cm polyester mesh halfcalendered. The calendered side was positioned face down towards the substrate, ie. M.G. (machine glazed) poster paper. The stencil was made from direct emulsion using a half-tone positive. The print was produced on an S.P.S. cylinder action screen printing press. The ink was dried through a two lamp S.P.S. U.V. dryer (rated at 300 watt per inch). The resultant dried print was a good half tone image of high definition.

20 However, this initial formulation, when tested, gave poor screen stability. This was improved, in a second embodiment, by the addition of n-vinyl pyrrolidone—a solvent miscible with water which also takes part in the curing reaction. A specific formulation of this second embodiment, which likewise has the resin amounting to 50% of the emulsion), is given in Example 2.

Example 2

Parts by weight

25			25
	Laromer* PE 55W ⁽¹⁾	85.3	
	Darocur* 1173 ⁽²⁾	2.0	
30	Aquadisperse Phthalo Blue GB EP ⁽³⁾	2.7	30
	n-vinyl pyrrolidone ⁽⁴⁾	10.0	

35 A composition as formulated in Example 2 was printed and dried in the same manner as for Example 1. The resultant dried print was a good half tone image of high definition.

40 Due to the relatively high price of this water-miscible solvent, i.e. the n-vinyl pyrrolidone, compared to the other materials used in the formulation, the final material cost was considered uneconomic. To offset this, a calcium carbonate extender was introduced into the composition to obtain a third embodiment with an acceptable raw material cost. A mixture of photoinitiators was also used in place of the single type. A specific formulation of this third embodiment, which likewise had the resin amounting to 50% of the emulsion, is given in Example 3.

Example 3

Parts by weight

45			45
	Emulsion Laromer* PE 55W ⁽¹⁾	63.3	
	Aquadisperse Phthalo Blue GB EP ⁽³⁾	2.7	
50	N Vinyl Pyrrolidone ⁽⁴⁾	5.0	50
	Omyalite* 95T Extender ⁽⁵⁾	20.0	
	Photoinitiator Irgacure* 651 ⁽⁶⁾	6.0	
55	Photoinitiator Quantacure* ITX ⁽⁷⁾	3.0	55

60 A composition formulated as in Example 3 was printed and dried in the same manner as for Example 1. The resultant dried print was a good half tone image of high definition. Samples of four colours Trichromatic yellow, magenta, cyan and black were made for container storage stability trials.

65 After four weeks storage, the magenta and black inks had gelled whereas the yellow and cyan were unchanged. Further work was carried out to improve storage stability. In order to retain screen stability and an economic raw material cost, a fourth embodiment was devised in which the n-vinyl pyrrolidone and the photoinitiator mixture were replaced by a solvent, ethoxy-propa-

not and a single initiator compound rather than the mixture of photoinitiators. The calcium carbonate extender was also omitted as this was not now required to obtain an acceptable raw material cost. A thickening agent was introduced to maintain the ink at a printable viscosity.

- 5 Slight improvements in screen stability were obtained with this embodiment by the introduction of small amounts of a humectant/surfactant compound and of a silicone emulsion lubricant. A specific formulation of this fourth embodiment, in which (as before) the resin amounted to 50% of the emulsion, is provided in Example 4. 5

Example 4

Parts by weight

10			10
	Laromer* PE 55W ⁽¹⁾	75.2	
	Darocur* 1173 ⁽²⁾	2.9	
15	Ethoxy Propanol ⁽⁸⁾	9.7	15
	Curlout Plus* ⁽⁹⁾	5.8	
	Alcoprint* PTF ⁽¹⁰⁾	0.5	
20	Alcoprint* PHL ⁽¹¹⁾	1.0	20
	Alcoprint PSJ ⁽¹²⁾	1.9	
	Aquadisperse Phthalo Blue GB EP ⁽³⁾	3.0	

25 25

A composition formulated as in Example 4 was printed and dried in the same manner as for Example 1. The resultant dried print was a good half tone image of high definition.

The storage stability of trichromatic yellow, magenta, cyan and black printing inks with this latest formulation were then retested and found to be satisfactory.

- 30 To provide a completely aqueous-based composition avoiding the use of any inflammable solvents, a fifth embodiment was devised in which the ethoxy propanol was replaced by a mixture of water and an acrylic monomer—Tripropylene glycol diacrylate (T.P.G.D.A.)—for maintaining the appropriate dispersion of the resin solids. A specific formulation of this fifth embodiment is provided in Example 5. 30

35 35

Example 5

Parts by weight

40	Laromer* PE 55W ⁽¹⁾	61.6	40
	Darocur* 1173 ⁽²⁾	3.1	
	Acrylic Monomer T.P.G.D.A. ⁽¹³⁾	7.7	
45	Water	15.4	45
	Curlout Plus* ⁽⁹⁾	5.7	
	Alcoprint* PTF ⁽¹⁰⁾	0.5	
	Alcoprint* PHL ⁽¹¹⁾	1.0	
50	Alcoprint* PSJ ⁽¹²⁾	2.0	50
	Aquadisperse* Phthalo Blue GB EP ⁽³⁾	3.0	

- 55 A composition formulated as in Example 5 was printed and dried in the same manner as for Example 1. The resultant dried print was a good half tone image of high definition. 55

All the above-mentioned tests were carried out using 60" x 40" (1.5m x 1m) machine glazed (M.G.) Poster Paper. It was found that when heavy deposits of colour were used across the whole area of the paper, a high degree of curl at the edges of the paper was experienced if the first colour printed down onto the paper was not a non-aqueous UV-curing ink (e.g. such as that of Example 6 below), or was not an organic solvent-based printing ink (e.g. such as that of Example 7 below), or was not an ink of a high solids/low water composition (e.g. such as that of Example 8 below), i.e. an ink which contains less than 20% water. 60

Example 6 (referred to above)

Parts by weight

5	Isol* Phthalo Blue GB PE 370 ⁽¹⁴⁾	1.5	5
	Synocure* 3101 ⁽¹⁵⁾	50.0	
	Acrylic Monomer T.P.G.D.A. ⁽¹³⁾	33.4	
10	Quantacure* ITX ⁽⁷⁾	2.9	10
	N. Methyl Diethanolamine ⁽¹⁷⁾	1.9	
	Irgacure 651 ⁽⁶⁾	5.7	
15	20cs Dimethyl Silicone Fluid ⁽¹⁶⁾	1.0	15
	Thickening Agent Cab-O-Sil* M5 ⁽¹⁸⁾	1.7	
	Matting Agent TS100 ⁽¹⁹⁾	1.9	

20 A composition formulated as in Example 6 was printed and dried in the same manner as for Example 1. The resultant dried print was a good half tone image of high definition.

Example 7 (referred to above)

Parts by weight

25			25
	Piccolastic* A5 ⁽²⁰⁾	1.67	
	Ethoxy Propanol ⁽⁸⁾	9.33	
30	N Propanol ⁽²¹⁾	4.33	30
	Di-octyl Phthalate ⁽²²⁾	1.67	
	Arcosolve* PM Acetate ⁽²³⁾	26.00	
35	Predisol* Phthalo Blue GBPC ⁽²⁴⁾	1.56	35
	Dispercel* Thixotrope 27E ⁽²⁵⁾	7.00	
	Xylene ⁽²⁶⁾	10.67	
40	Shellsol* A ⁽²⁷⁾	16.00	40
	Ethocel* 7 CPS ⁽²⁸⁾	15.33	
	GB Ester ⁽²⁹⁾	6.44	

45 A composition formulated as in Example 7 was printed through a screen made from 140 threads per cm polyester mesh. The stencil was made from direct emulsion using a half tone positive. The print was produced on a Svecia cylinder action screen printing press. The ink was dried through a warm air jet dryer. The resultant dried print was a good half tone image of high definition.

Example 8 (referred to above)

Parts by Weight

55	Darocur* 1173 ⁽²⁾	3.0	55
	Water	15.0	
	Aquadisperse Phthalo Blue GB EP ⁽³⁾	3.0	
60	UV Oligomer 85-578/79 ⁽³⁰⁾	77.5	60
	Alcoprint* PTF ⁽¹⁰⁾	0.5	
	Silicone Antifoam S.882 ⁽³¹⁾	1.0	

A composition formulated as in Example 8 was printed and dried in the same manner as for Example 1. The resultant dried print was a good half tone image of high definition.

It was unexpectedly found that once the first (cyan) ink had been printed in a non-aqueous UV-curing printing ink (e.g. of Example 6), or in an organic solvent-based printing ink (e.g. of Example 7), or in a high solid, low screen ink (e.g. of Example 8) having 20% or less water, then water based inks according to Examples 1 to 5—which contain at least 40% water—could nevertheless be used as additional colours without producing unacceptable curl of the paper, i.e. without preventing feeding of the printed sheet again through the screen printing machine.

The water-based inks of Examples 1 to 5, when cured only by U.V. radiation, were found to have a wet rub-resistance not adequate for all purposes, and to have a variable gloss level. Experiments were carried out with infra red heating just before U.V. curing of the water-based inks was effected. This technique produced prints with good wet rub-resistance and with a substantially uniform level of gloss. It is thought that this was due to the removal of excess water by the infra-red heating. It was also found that more efficient water removal could be achieved by using a jet air dryer to force cold air over the print. It is considered that excess water might be removed, additionally or alternatively, by microwave or radio frequency drying. Tests were conducted in pasting up the individual sheets to produce hoarding posters, and starch based pastes (obtained from Wilsons Adhesives and Morris Greenhaugh) were used for these tests. The surface of the final prints produced in accord with the above Examples was found to accept the starch pastes used by bill-posters more readily than prints printed with the conventional screen inks which are currently in general use. Prints produced with the water-based inks of Examples 1 to 5, when dried only by UV radiation, showed excellent adhesion properties with the starch adhesives. Such prints, when dried both by infra-red and by UV radiation, showed a reduction in adhesion properties but this was still an improvement on that attainable with multi-colour prints produced with the standard organic solvent based screen printing inks. Nevertheless, by subjecting the final prints that had been dried by both infra-red and UV radiation to corona discharge, this reduction in adhesion properties was overcome and prints with good gloss and wet-rub resistance were still obtained. In a preferred example, prints dried by infra-red and UV radiation were treated to 73 dynes/cm using a Sherman Treaters Corona Discharge Machine. These prints showed the same excellent adhesion properties that were obtained by just drying with UV radiation.

Notes

* means Trade Mark

1. Laromer* PE 55W is a 50% emulsion of a polyester acrylate in water obtainable from B.A.S.F.
2. Darocur* 1173 is a Hydroxy-2-methyl-1-propan-1-one obtainable from E. Merck
3. Aquadisperse* Phthalo Blue GB EP is an aqueous dispersion of pigment Blue 15 obtainable from Tennant-K.V.K.
4. n-vinyl pyrrolidone is a UV reactive solvent obtainable from B.A.S.F.
5. Omyalite* 95T is a calcium carbonate extender obtainable from Croxton & Garry.
6. Irgacure* 651 is Benzil Dimethyl-Ketal obtainable from Ciba Geigy.
7. Quantacure* ITX is Isopropylthioxanthone obtainable from Ward Blenkinsop.
8. Ethoxy Propylene Glycol Ether obtainable from B.P. Chemicals.
9. Curlout* Plus is a modified acrylic solution polymer obtainable from American Carbonyl Inc.
10. Alcoprint* PTF is an acrylic copolymer in mineral oil thickener obtainable from Allied Colloids.
11. Alcoprint* PHL is a humectant and surfactant blend obtainable from Allied Colloids.
12. Alcoprint* PSJ is a silicone emulsion softener/lubricant obtainable from Allied Colloids.
13. T.P.G.D.A. is a Tripropylene Glycol Diacrylate obtainable from Degussa.
14. Isol* Phthalo Blue GBP 370 is Pigment Blue 15 obtainable from Tennant K.V.K. Ltd.
15. Synocure* 3101 is an epoxy acrylate obtainable from Cray Valley Products Limited.
16. Dimethyl Silicone fluid 20csV viscosity obtainable from Basildon Chemical Company Limited.
17. N-Methyl Diethanolamine is a Tertiary Amine, obtainable from B.A.S.F.
18. Cab-O-Sil* M5 is Fumed Silica obtainable from Cabot Carbon.
19. TS100 is a Silica Matting Agent obtainable from Degussa.
20. Piccolastic* is a liquid styrene resin obtainable from Hercules Ltd.
21. N Propanol is obtainable from B.P. Chemicals.
22. Di-octyl Phthalate is obtainable from Charles Tennant (London) Ltd.
23. Arcosolve* PM Acetate is propylene glycol monomethyl ether acetate obtainable from Hays Chemical UNALCO.
24. Predisol* Phthalo Blue GBPC is a nitrocellulose dispersion of pigment Blue 15 obtainable from Tennant KVK.

25. Dispercel* Thixotrope 27E is a nitrocellulose dispersion of Bentone 27E gellant.
 26. Xylene is obtainable from Shell Chemicals
 27. Shellsol* A is an isomeric mixture of trimethyl benzenes obtainable from Shell Chemicals.
 28. Ethocel* 7 CPS is ethyl cellulose resin obtainable from Dow Chemicals.
 5 29. GB Ester is butyl glycolate obtainable from Wacker Chemicals. 5
 30. UV Oligomer 85-578/79 is a UV resin with 5% water content available from Hans Rahn & Co, Zurich.
 31. Silicone Antifoam S.882 is a water miscible antifoam available from Wacker Chemicals.

10 CLAIMS

10

1. A method of silk screen printing on a sheet of paper or board, characterised in that a first silk screen printing is effected on the sheet utilising a printing ink that produces minimal curl, and in that at least one subsequent silk screen printing is effected on the sheet utilising a water-based printing ink.
- 15 2. A method according to Claim 1, characterised in that the first silk screen printing is in a first colour and the or each said subsequent printing is in a different colour. 15
3. A method according to Claim 1 or Claim 2, characterised in that the printing ink for said first screen printing comprises a non-aqueous printing ink that is at least partially curable by irradiation.
- 20 4. A method according to Claim 3, characterised in that the non-aqueous printing ink that is curable by irradiation comprises one or more photoinitiators and is curable by irradiation comprising electromagnetic radiations in the ultra-violet light waveband. 20
5. A method according to Claim 3, characterised in that the said non-aqueous printing ink is curable by irradiation with an electron beam.
- 25 6. A method according to Claim 3 or Claim 4, characterised in that the non-aqueous printing ink that is curable by irradiation comprises a screen printing ink substantially as described in Example 6. 25
7. A method according to Claim 1 or Claim 2, characterised in that the printing ink for said first screen printing comprises an organic solvent-based printing ink.
- 30 8. A method according to Claim 7, characterised in that the organic solvent-based printing ink comprises a screen printing ink substantially as herein described in Example 7. 30
9. A method according to Claim 1 or Claim 2, characterised in that the printing ink for said first screen printing comprises an aqueous ink of low water and high solids content.
- 35 10. A method according to Claim 9, characterised in that the printing ink for said first screen printing comprises a screen printing ink substantially as described in Example 8. 35
11. A method according to any preceding Claim, characterised in that said water-based ink for the or each said subsequent screen printing comprises at least 40% water.
- 40 12. A method according to any preceding Claim, characterised in that the or each said subsequent screen printing is effected utilising a water-based printing ink that is at least partially curable by irradiation. 40
13. A method according to any preceding Claim, characterised in that the water-based printing ink for the or each said subsequent screen printing has a composition comprising one or more photoinitiators and is at least partially curable by irradiation comprising electromagnetic radiations in the ultra-violet light waveband.
- 45 14. A method according to any one of Claims 1 to 12, characterised in that the water-based ink for the or each said subsequent screen printing is at least partially curable by irradiation with an electron beam. 45
15. A method according to any preceding Claim, characterised in that the each water-based printing ink for the or each said subsequent screen printing is subjected to heat or to thermal radiation prior to curing.
- 50 16. A method according to any preceding Claim, characterised in that the water-based printing ink for the or each said subsequent screen printing is subjected to electromagnetic radiations in the infra-red light waveband prior to curing. 50
17. A method according to any preceding Claim, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises an unsaturated acrylate resin.
- 55 18. A method according to any preceding Claim, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises a polyester acrylate resin. 55
19. A method according to any preceding Claim, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises an emulsion of a resin in water.
- 60 20. A method according to Claim 19, characterised in that the emulsion has the said resin wholly, or at least substantially, in dispersed phase and wholly or at least substantially insoluble in water, the water being the continuous phase of the emulsion. 60
21. A method according to Claim 19 or Claim 20, characterised in that the resin comprises between 30% to 60% of the emulsion.
- 65 22. A method according to any one of Claims 19 to 21, characterised in that the resin 65

comprises 50% of the emulsion.

23. A method according to any one of Claims 1 to 22, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises a composition substantially as herein described in Example 1.

5 24. A method according to any one of Claims 1 to 22, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises a composition substantially as herein described in Example 2. 5

25. A method according to any one of Claims 1 to 22, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises a composition substantially as herein described in Example 3. 10

26. A method according to any one of Claims 1 to 22, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises a composition substantially as herein described in Example 4. 10

27. A method according to any one of Claims 1 to 22, characterised in that the water-based printing ink for the or each said subsequent screen printing comprises a composition substantially as herein described in Example 5. 15

28. A method according to any preceding Claim employed to screen print a plurality of colours upon a sheet and characterised in that, after printing, the printed sheet is subjected to corona discharge to render the sheet suitable for mounting by use of a starch-based adhesive.